

 <p>Procesadora de Boratos Argentinos S.A.</p>	SPECIFICATIONS		Código Documento E-LBT55		
	Specifications of Tincal LBT – 55		Rev.	Hoja	Total
			7	1	1

SUSBSTANCES	COMPOSITION (%)		
	Typical value	Minimum	Maximum
	<i>Content</i>		
B₂O₃	55,0	54,0	58,0
Na₂O	20,0	18,0	24,0
CaO	5,0	3,0	6,0
	<i>Impurities</i>		
Cl⁻	-----	-----	0,05
SO₄⁼	-----	-----	0,05
Insolubles (SiO₂, Al₂O₃)	7,0	-----	10,0
MgO	0,5	-----	0,7
Fe₂O₃	0,50	-----	0,60
PPC	10,0	-----	15,0

Granulometry	Typical value	Minimum	Maximum
% pass mesh # ASTM 6	100	99	100
% pass mesh # ASTM 270	5	-----	25