

## PLATINUM/RHODIUM FLAKE 90 / 10 6490 0177

### PRODUCT DESCRIPTION

- Coprecipitated Platinum/Rhodium Flake

### KEY FEATURES

- Fine flake

### APPLICATIONS

- High reliability fired systems
- Sensor components
- Heating elements

### TYPICAL PROPERTIES

#### PHYSICAL DATA:

Surface Area: 2.0 - 4.0 m<sup>2</sup>/gm


Firing residue:  
850°C: ≥ 97.0 %

#### Particle size distribution:

10 % 0.4 - 1.0 μm

50 % 1.0 - 4.0 μm

90 % 5.0 - 9.0 μm



For more technical information please contact Dietmar Mann from our applied technology team in our EM – department.

**phone: 49 – 61 81/59 – 40 78**  
**fax: 49 – 61 81/59 – 40 02**

---

Ferro Corporation  
Electronic Material Systems  
3900 So. Clinton Ave.  
So. Plainfield, NJ 07080  
USA  
(908) 561-1100  
FAX: (908) 756-7176

Ferro Corporation  
Rodenbacher Chaussee 4  
P. O. Box 1351  
D-63403 Hanau-Wolfgang  
GERMANY  
49.6181.59.3090  
FAX: 49.6181.59.3129

Ferro Corporation  
Shinjuku Monolith 16F  
2-3-1 Nishi-Shinjuku  
Shinjuku-Ku Tokyo 163-0916  
JAPAN  
81.3.5323.7322  
FAX: 81.3.5323.7396

---

**DISCLAIMER:** Reasonable care has been taken in the preparation of this information, but **FERRO EXTENDS NO WARRANTIES, MAKES NO REPRESENTATIONS AND ASSUMES NO RESPONSIBILITY AS TO ACCURACY OR SUITABILITY OF THIS INFORMATION OF THIS PRODUCT FOR ANY PURCHASER'S OR USER'S USE OR FOR ANY CONSEQUENCE OF ITS USE. FERRO DISCLAIMS ANY WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR ANY PARTICULAR USE.** All statements, technical information and recommendations contained herein are based on Seller's or Manufacturer's test and the test of others, and are believed to be accurate, but no guarantee of accuracy is made. Judgment as to the suitability of information herein or the user's purposes are necessarily the user's responsibility. Users shall determine the suitability of the products for their own intended application.

Users assume all risk of use or handling whether or not in accordance with any statements or recommendation of the seller or manufacturer, Liability, if any, is and shall be limited to the replacement of such quantity of material proved not to conform to specifications as set out in product specification. Statements concerning the possible use of these products are not intended as recommendation to use these products in infringement of any patent. No guarantee is made that any use of the products does not infringe third-party intellectual property or patent rights anywhere in the world.

---

Ferro Electronic Material Systems  
[www.ferro.com](http://www.ferro.com)