

3349 ND
Silver Conductor

Description: For many years, Ferro has been the leading supplier of thick film silver inks designed for making contact to the n-doped silicon front face of photovoltaic devices. Achieving good adhesion with an excellent ohmic contact to this shallow junction is critical in the production of high efficiency cells. Ferro Electronic Materials has produced a number of different formulations for this application. It has been our experience that each cell type has variations in junction depth, dopant concentration and silicon orientation. For this reason, we suggest that a manufacturer new to our product test variations of these formulations, in order to capture the sometimes-subtle advantages that one of them may offer for a particular cell type. For similar reasons, our recommended firing profile is meant to be taken as a starting point only and it is absolutely essential that a matrix of profiles be tested to achieve optimum output.

3349 ND is a silver based thick film conductor paste which contains phosphorous diffusion source in its formulation. It has proved to be extremely successful in firing through a wide variety of anti-reflective and passivation coatings and displays enhanced contact resistance performance over a wide range of temperatures and firing conditions.

Thinning: Thinning is not recommended, since the paste is supplied at the correct viscosity for application. Contact your local Ferro Representative for appropriate solvent details, should thinning become necessary to replace solvent lost through evaporation.

Paste Storage & Shelf Life: The paste should be stored in tightly capped containers, in a cool, dry place away from direct sunlight. Properly stored material will have a shelf life in excess of 6 months.

Typical Properties

Solids:	77.4-79.7%
Viscosity:	900 – 1,100 poise @ 9.6s ⁻¹
Fineness of Grind:	14/11 μm
Print Thickness	
Dry:	16-25 μm
Fired:	8-14 μm
Standard Test Print Conditions:	325#, screen 25 μm emulsion, 0.5 to 1.5mm snap off
Standard Test Drying Conditions:	150°C
Standard Test Firing Conditions*:	600°C/9-11 minutes peak
Visual Appearance:	Smooth, no lumps, min. 95% density no blowholes
Resistivity:	<2mΩ/sq (Normalized to 25 μm)
Solderability:	90% coverage, 3 second dip RMA flux Sn 62 @ 215±5°C
Recommended Thinner:	0800

*Note: This profile is used for product characterization only, in production, infrared firing profiles with spiked peak temperatures in the range of 720-850°C are commonly used. Exact process conditions will depend on many factors and will need to be optimized by each individual user.

Rev. 1200

www.ferro.com

DISCLAIMER: Reasonable care has been taken in the preparation of this information, but **FERRO EXTENDS NO WARRANTIES, MAKES NO REPRESENTATIONS AND ASSUMES NO RESPONSIBILITY AS TO ACCURACY OR SUITABILITY OF THIS INFORMATION OF THIS PRODUCT FOR ANY PURCHASER'S OR USER'S USE OR FOR ANY CONSEQUENCE OF ITS USE. FERRO DISCLAIMS ANY WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR ANY PARTICULAR USE.** All statements, technical information and recommendations contained herein are based on Seller's or Manufacturer's test and the test of others, and are believed to be accurate, but no guarantee of accuracy is made. Judgment as to the suitability of information herein or the user's purposes are necessarily the user's responsibility. Users shall determine the suitability of the products for their own intended application.

Users assume all risk of use or handling whether or not in accordance with any statements or recommendation of the seller or manufacturer. Liability, if any, is and shall be limited to the replacement of such quantity of material proved not to conform to specifications as set out in product specification. Statements concerning the possible use of these products are not intended as recommendation to use these products in infringement of any patent. No guarantee is made that any use of the products does not infringe third-party intellectual property or patent rights anywhere in the world.