

CerDeCoat

Opaque Frits

Reference	Product Type	Glossy	Matt	T T (C)	T W (C)	Thermal expansion COE(*10E-7/C)	Firing Temperature (C)	Comments	SiO2	Al2O3	B2O3	Na2O	K2O	Li2O	CaO	MgO	ZrO2	ZnO	BaO	PbO	F	TiO2	Others	
CE FBC 290/435	Zircon frit	x		580	625	170	940-1000	Soft	***	**	***	**	*		**	*	**	**						
CE FBC 394	Zircon frit	x		610	695	173	970-1050		***	**	***	**	*		**	*	***	*						
CE FBC 1107003	Zircon frit	x		620	670	185	920-980		***	**	***	**	*		**	*	***	*						
CE FBC 396	Zircon frit	x		620	700	155	1000-1060	Low expansion	***	**	***	**	**		**		**	*	*					
CE FBC 32	Zircon frit with lead	x		580	645	182	980-1020		***	**	***	**	*		**	*	***	*		*				

The information and statements contained herein are provided free of charge. They are believed to be accurate at the time of publication, but Ferro makes no warranty with respect thereto, including but not limited to any results to be obtained or the infringement of any proprietary rights. Use or application of such information or statements is at user's sole discretion, without any liability on the part of Ferro. Nothing herein shall be construed as a license of our recommendation for use, which infringes upon any proprietary rights. All sales are subject to Ferro's General Conditions of Sale and Delivery. 04/2004

