

CerDeCoat

Opaque Glazes

Reference	Product Type	Glossy	Matt	T T (C)	T W (C)	Thermal expansion COE(*10E-7/C)	Firing Temperature (C)	Fineness on 325 mesh (%)	SiO2	Al2O3	B2O3	Na2O	K2O	Li2O	CaO	MgO	ZrO2	ZnO	BaO	PbO	F	TiO2	Others
CE VTR 81	Old effect	x		550	630	175	980-1020°C	<5	***	***	**	*			*	*	***	*	***				
CE VBCM 68	Opaque		x	610	715	184	1020-1050°C	0,5-2,5	***	***	**	**	*		**	*	***	***	*	**			
CE VBCM 419	Opaque		x	625	750	190	1000-1040°C	1.0-3.0	***	***	**	**	**		***		**	**	*				
CE VBC 12	Opaque	x		615	680	170	1000-1030°C	0,5-2,5	***	***	***	**	*		**	*	***	*					
CE VBC 13	Opaque	x		610	680	173	980-1020 ^a °C	0,5-2,5	***	**	***	**	*		**	*	***	*					
CE VBC 32	Opaque w/lead	x		585	650	179	960-1000 ^a °C	0.5-2.5	***	**	***	**	*		**	*	***	*	*				
CE VBC 142	Opaque	x		560	640	202	920-980°C	0,5-2,5	***	**	***	**	**		**		***	**			*		
CE VBC 386	Opaque	x		620	710	174	1030-1060°C	1.0-3.0	***	***	***	**	*		**	*	***	**	*				
CE VBSC 78	Opaque		x	670	800	184	1160-1200°C	2,5-4,5	***	***	*	*	**		***	**	***	**	*				
CE VBSC 97	Opaque	x		720	830	176	1200-1220°C	<0,5	***	***		*	**		***		***	**	**				
CE VBSC 504	Opaque	x		665	755	189	1150-1180°C	0.5-2.5	***	***	**	**	**		***	*	***	*		*			

The information and statements contained herein are provided free of charge. They are believed to be accurate at the time of publication, but Ferro makes no warranty with respect thereto, including but not limited to any results to be obtained or the infringement of any proprietary rights. Use or application of such information or statements is at user's sole discretion, without any liability on the part of Ferro. Nothing herein shall be construed as a license of our recommendation for use, which infringes upon any proprietary rights. All sales are subject to Ferro's General Conditions of Sale and Delivery. 04/2004

