

 <p>Procesadora de Boratos Argentinos S.A.</p>	<b>SPECIFICATIONS</b>		Código Documento E-LBU60		
	Specifications of Ulexite LBU – 60		Rev.	Hoja	Total
			7	1	1

SUBSTANCES	COMPOSITION ( % )		
	Typical value	Minimum	Maximum
	<i>Content</i>		
<b>B<sub>2</sub>O<sub>3</sub></b>	60,0	59,0	62,0
<b>Na<sub>2</sub>O</b>	10,5	8,5	12,0
<b>CaO</b>	19,5	18	21
	<i>Impurities</i>		
<b>Cl<sup>-</sup></b>	-----	-----	0,05
<b>SO<sub>4</sub><sup>=</sup></b>	-----	-----	0,05
<b>Insolubles (SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>)</b>	6,5	-----	9,0
<b>MgO</b>	0,4	-----	0,7
<b>Fe<sub>2</sub>O<sub>3</sub></b>	0,28	-----	0,35
<b>PPC</b>	2,4	-----	6,0

Granulometry	Typical value	Minimum	Maximum
% pass mesh # ASTM 6	100	99	100
% pass mesh # ASTM 140	15	-----	40