
















美国无铅钢化玻璃颜料

美国无铅钢化玻璃颜料主要用于装饰建筑玻璃、幕墙玻璃和家具玻璃。其主要组成为无铅熔剂和无机色剂。其颜料中铅和镉的总含量小于 1000 ppm . 基础熔剂的膨胀系数 $80 \pm 2 \times 10^{-7} \text{ } ^\circ\text{C}^{-1}$, 最低烤烧温度 621 $^\circ\text{C}$

1. 产品编号:

产品编号	产品颜色	产品编号	产品颜色
25-8009		26-8025	
27-8037		27-8039	
29-8029		23-8034	
23-8035		20-8079	
20-8093		20-8101	
20-8099		20-8090	
20-8155		24-8029	
20-8089			

2. 性能特点

印刷粘度 18000 到 24000 cps (10 rpm, 23.8 $^\circ\text{C}$)

印刷网目 43 T 到 77 T (110-190 目/英寸)

刮板硬度 60 到 75 度

湿颜料层厚度 1.0 to 2.0 mils / 25 to 50 微米

2.3 干燥性能

烘干方法 适合传统干燥, 红外干燥, 自然干燥