



NS 33-501 Front Contact Silver for SiN_x Passivated Solar Cells

Description: NS 33-501 silver conductor paste is designed for contacting p/n⁺ type crystalline silicon solar cells passivated with SiN_x coatings with thicknesses between 750–900 Å. The rheology of NS 33-501 minimizes line spreading during printing. When fired, this screen printable ink yields very low bulk and contact resistivity, which results in high a fill factor and energy conversion efficiency. During the firing process the glasses and additives contained in the inks

react with silicon nitride to form a low resistance contact while providing good adhesion to the wafer and excellent solderability. The ink provides very good electrical contact to n+ surfaces passivated with SiN_x. NS 33-501 is able to contact emitters from 40-55 Ω/square. The conductor is compatible with all Ferro rear silver pastes as well as lead free and low bow aluminum pastes. NS 33-501 also has the ability to fire through TiO₂ ARC.

Typical Properties

	NS 33-501
Viscosity (Pa·s) ¹ :	280–360
Solids Content:	83.0–86.0%
Fineness of Grind:	<14/11 μm
Dried Thickness:	20–25 μm
Fired Thickness:	12–15 μm
Line Resolution:	100–150 μm
Resistivity ² (milliohms/square):	< 2
Drying Profile ³ :	250–300°C, <60 seconds
Firing ³ :	810–940°C, < 1–3 seconds
Recommended Thinner	0800

All properties are target values and are not meant to represent product specifications

Notes:

¹Viscosity as measured on Brookfield model HBT cone/plate viscometer; 9.6 reciprocal seconds, 1.565° cone, 25°C.

²Milliohms/sq. at 25 μm.

³Recommended set points °C in infrared firing furnace.

Product Advantages:

- RoHS compliant⁴
- Cadmium free⁵
- Forms excellent contact on 40–55 Ω/square emitters
- Reduced contact resistance & higher aspect ratio yield greater power output
- Wide processing window, fires through SiN & TiO₂ ARCs
- Hot Melt & conventional printing versions available

www.ferro.com

DISCLAIMER: Reasonable care has been taken in the preparation of this information, but FERRO EXTENDS NO WARRANTIES, MAKES NO REPRESENTATIONS AND ASSUMES NO RESPONSIBILITY AS TO ACCURACY OR SUITABILITY OF THIS INFORMATION OF THIS PRODUCT FOR ANY PURCHASER'S OR USER'S USE OR FOR ANY CONSEQUENCE OF ITS USE. FERRO DISCLAIMS ANY WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR ANY PARTICULAR USE. All statements, technical information and recommendations contained herein are based on Seller's or Manufacturer's test and the test of others, and are believed to be accurate, but no guarantee of accuracy is made. Judgment as to the suitability of information herein or the user's purposes are necessarily the user's responsibility. Users shall determine the suitability of the products for their own intended application.

Users assume all risk of use or handling whether or not in accordance with any statements or recommendation of the seller or manufacturer. Liability, if any, is and shall be limited to the replacement of such quantity of material proved not to conform to specifications as set out in product specification. Statements concerning the possible use of these products are not intended as recommendation to use these products in infringement of any patent. No guarantee is made that any use of the products does not infringe third-party intellectual property or patent rights anywhere in the world.



NS 33-501 Front Contact Silver for SiN_x Passivated Solar Cells

Processing Recommendations

Printing: It is recommended that the paste temperature be between 20–25°C prior to printing, and it is advisable to control the ambient room temperature within ± 2° to insure consistent printing results. The printing area should be clean and well-ventilated.

Screen: 280–325 mesh screen with a 20–25 μm emulsion thickness is recommended. Wire diameter is 20–25 μm with a mesh orientation of 45°.

Drying: The ink can be dried in an Infrared or conventional dryer under a wide range of conditions. Inks are typically dried in an IR dryer with set points of 250–300°C in less than 60 seconds.

Soldering: Recommended soldering conditions (ribbons) are 290°C for 96.5Sn/3.5Ag; and 220°C for 62Sn/36Pb/2Ag.

Firing: An Infrared fast process furnace with three or more firing zones and belt speeds of > 200 inches per minute is highly recommended, although the product may be fired in a variety of furnaces with belt speeds > 120 inches per minute. Optimum firing conditions must be established by the customer based on the cell configuration, thickness, and manufacturing process. Peak set point temperatures between 810–940°C with a dwell time above 700°C ranging from > 1 to 3 seconds is typical.

Compatibility: Ferro has tested this material according to the recommended processing conditions described here, however, it is imperative that customers evaluate the material in their manufacturing process and conditions to insure suitability for their intended use. Ferro technical personnel can help facilitate testing, and can assist with integration into customer manufacturing processes.

Thinning: Thinning is not recommended, since the paste is supplied at the correct viscosity for application. Contact your local Ferro Representative for appropriate solvent details, should thinning become necessary to replace solvent lost through evaporation.

Paste Storage & Shelf Life: The paste should be stored in tightly capped containers in a cool (5–30°C) dry place away from direct sunlight. When properly stored, unopened material will have a shelf life of up to 6 months.

Notes:

⁴Complies with EU Directives on Restriction of the use of Hazardous Substances (RoHS; 2002/95/EC) and Waste from Electrical and Electronic Equipment (WEEE; 2002/96/EC). Current exemptions allow lead contained in the glass system of thick film materials used in electronic components. In anticipation of future amendments and more stringent environmental regulations, Ferro continues to expand its range of Lead Free⁵ materials.

⁵Initial product composition was certified by SGS laboratories to be below the detection level for cadmium. This conductor paste is not routinely analyzed for cadmium content and is not the basis for product specification or warranty.

Rev. 08/09

Vista, CA, USA
760-305-1000

Tsukuba, Japan
+81 29-889-2144

Suzhou, China
+86 512-62562258

Hanau, Germany
+49 61-81594739

www.ferro.com

DISCLAIMER: Reasonable care has been taken in the preparation of this information, but FERRO EXTENDS NO WARRANTIES, MAKES NO REPRESENTATIONS AND ASSUMES NO RESPONSIBILITY AS TO ACCURACY OR SUITABILITY OF THIS INFORMATION OF THIS PRODUCT FOR ANY PURCHASER'S OR USER'S USE OR FOR ANY CONSEQUENCE OF ITS USE. FERRO DISCLAIMS ANY WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR ANY PARTICULAR USE. All statements, technical information and recommendations contained herein are based on Seller's or Manufacturer's test and the test of others, and are believed to be accurate, but no guarantee of accuracy is made. Judgment as to the suitability of information herein or the user's purposes are necessarily the user's responsibility. Users shall determine the suitability of the products for their own intended application.

Users assume all risk of use or handling whether or not in accordance with any statements or recommendation of the seller or manufacturer. Liability, if any, is and shall be limited to the replacement of such quantity of material proved not to conform to specifications as set out in product specification. Statements concerning the possible use of these products are not intended as recommendation to use these products in infringement of any patent. No guarantee is made that any use of the products does not infringe third-party intellectual property or patent rights anywhere in the world.